





## **Color Guide**

## **PVDF Paint System**












**Burnished Slate (49)** TE = 0.85 SR = 0.30










## MS Colorfast45® Paint System


SRI = 30





















SR = 0.31 TE = 0.87



SRI = 31

SR = 0.30 TE = 0.88



**SRI = 33** 



TE = 0.87

**SRI = 31** 

SR = 0.30







SR = 0.32 TE = 0.87



Ash Grey (25) SR = 0.37 TE = 0.88SRI = 40

Forest Green (26) TE = 0.87 SR = 0.27 SRI = 27

Patina Green (58) TE = 0.86 SR = 0.29 SRI = 29

SR = 0.30TE = 0.88SRI = 31


(Color Code) • SR = Initial Solar Reflectance • TE = Thermal Emittance • SRI = Solar Reflectance Index



All Colors Meet or Exceed ENERGY STAR® Steep Slope Requirements

<sup>1</sup> Meets or Exceeds ENERGY STAR® Low Slope Requirements

SRI = 32



Panels are also available in other gauges, please inquire. Not all colors and gauges are stocked at all branches. Color samples are close representations but are limited by processing and viewing conditions. Actual samples are available by request. For all specific warranty, application, installation and technical information regarding these products, contact your sales representative.

| PVDF PAINT PERFORMANCE |             |  | MS Colorfast45® Paint Performance |             |  |
|------------------------|-------------|--|-----------------------------------|-------------|--|
| Salt Spray Resistance  |             |  | Salt Spray Resistance             |             |  |
| ASTM B 117             | 1,000 Hours | Creep from scribe no more than 1/8", no blisters | ASTM B 117                        | 1,000 Hours | Creep from scribe no more than 1/8", no blisters |
| Humidity Resistance    |             |  | Humidity Resistance               |             |  |
| ASTM D 2247            | 2,000 Hours | No blisters, cracking or peeling                 | ASTM D 2247                       | 1,200 Hours | No blisters, cracking or peeling                 |
| Abrasion Resistance    |             |  | Abrasion Resistance               |             |  |
| <b>ASTM D 968</b>      | Method A    | 65 ± 5 liters/mil falling sand                   | ASTM D 968                        | Method A    | 30 liters/mil falling sand                       |
| Chalk Resistance       |             |  | Chalk Resistance                  |             |  |
| ASTM D 4214            | 2,000 Hours | No chalking greater #8 rating                    | ASTM D 4214                       | 2,000 Hours | No chalking greater #8 rating                    |

11-2015 1095



Bay City, MI: 888.777.7640 Deer Lake, PA: 800.544.2577 Denver, CO: 800.289.7663 Detroit Lakes, MN: 888.594.1394 Fort Smith, AR: 877.452.3915 Independence, MO: 800.747.0012 Jacksonville, FL: 800.394.4419 Jefferson, OH: 800.321.5833 Mocksville, NC: 800.228.6119 Nashville, TN: 800.251.8508 Rock Island, IL: 800.747.1206 Rogers, MN: 800.328.9316 Sellersburg, IN: 800.999.7777 Sioux Falls, SD 888.299.0024 Temple, TX: 800.543.4415

metalsales.us.com